

BELLINA CERAMIC TILE



## BELLINA CERAMIC TILE



3' x 13' BELLINA GREY BULLNOSE  
46-186



3' x 10' BELLINA GREY BULLNOSE  
56-073



13' x 13' BELLINA GREY FLOOR TILE  
46-140



10' x 16' BELLINA GREY WALL TILE  
56-044



3' x 8' BELLINA GREY BULLNOSE  
52-214




8' x 10' BELLINA GREY WALL TILE  
52-166



2' x 2' BELLINA MULTI MOSAICS  
46-144

## BELLINA CERAMIC TILE



3" x 13" BELLINA CREAM BULLNOSE  
46-187



3" x 10" BELLINA CREAM BULLNOSE  
56-074



13" x 13" BELLINA CREAM FLOOR TILE  
46-142



10" x 16" BELLINA CREAM WALL TILE  
56-046



3" x 8" BELLINA CREAM BULLNOSE  
52-215



8" x 10" BELLINA CREAM WALL TILE  
52-168

## BELLINA CERAMIC TILE

### PACKAGING INFORMATION

DESCRIPTION	ITEM CODE		LBS/BOX	PCS/BOX	SQFT/BOX	BOXES/SKID	SQFT/SKID
	GREY	CREAM					
8" x 10" BELLINA WALL TILE	52-166	52-168	27.05	20	10.76	92	989.92
3" x 8" BELLINA BULLNOSE	52-214	52-215	12.58	30	N/A	105	3150 pcs.
10" x 16" BELLINA WALL TILE	56-044	56-046	30.86	10	10.76	72	774.72
3" x 10" BELLINA BULLNOSE	56-073	56-074	15.62	25	N/A	98	2450 pcs.
13" x 13" BELLINA FLOOR TILE	46-140	46-142	43.79	11	12.91	58	748.90
3" x 13" BELLINA BULLNOSE	46-186	46-187	20.83	21	N/A	84	1764 pcs.
2" x 2" BELLINA MULTI MOSAICS	46-163	46-163	39.33	10	11.74	48	563.52

### GENERAL SPECIFICATIONS

DESCRIPTION	METHOD	UNIT	13" x 13"
THICKNESS		mm – in	7.6 mm – 5/16"
WATER ABSORPTION	EN ISO 10545-3	( % )	≤ 3
ABRASION RESISTANCE	EN ISO 10545-7	(PEI)	3
SCRATCH HARDNESS		(Mohs)	5
BREAKING STRENGTH	EN ISO 10545-4	(lbf)	≥ 250
CHEMICAL RESISTANCE	EN ISO 10545-13	(GL)	Class A – Resistant
FROST RESISTANCE	EN ISO 10545-12		Resistant
STATIC COEFFICIENT OF FRICTION (WET)	ASTM C-1028	(μ)	< 0.60
STATIC COEFFICIENT OF FRICTION (DRY)	ASTM C-1028	(μ)	≥ 0.90
DCOF (WET)	ANSI B101.3		< 0.42
SHADE VARIATION			V2